

| Legendă | |
|----------------|--|
| ARV | Acid resistance veil |
| CCP | Color change possible |
| CCSR | Check compatibility solvent/resin |
| CR | Classical recommendation |
| CU | Contact US |
| DSV | Double synthetic veil |
| DSV-AC | Double synthetic veil + anticorrosion layer |
| DVC | Double veil ("C" Type) |
| LOS | limit of solubility |
| PBBO | Prefer to cure with BPO |
| TC | TEMPORARY CONTACT (72h / 40°C per year maxi) , after contact , clean and check the aspect of laminate |

| Substanțe chimice | Legendă | Concentrație % | Temperatură |
|--|----------------|-----------------------|--------------------|
| 1-Methoxy-2-Propanol | CR | 100 | 20 |
| 2,2-Butoxyethoxyethanol (DOWANOL DB) | CR | 100 | 40 |
| 2,2-Dimethyl Thiazolidine | CR | 1 | 80 |
| 2,4-Dichlorophenoxyacetic Acid(Acid, Salts, Esters and Formulations) | CCSR | 100 | 50 |
| 2-Butoxyethanol (DOWANOL EB) | CR | 20 | 50 |
| | CR | 100 | 40 |
| 2-Chloro-2-methylpropane | CR | 100 | 25 |
| 2-Ethylhexyl Alcohol | CR | 100 | 80 |
| 2-methoxyethanol | CR | 100 | 25 |
| 3-methyl-1-butanol | CR | 100 | 0 |
| Acetaldehyde | CR | 20 | 40 |
| | CR | 100 | 0 |
| Acetic Acid | CR | 10 | 100 |
| | CR | 25 | 100 |
| | CR | 50 | 80 |
| | CR | 75 | 60 |
| Acetic acid Vapour | CR | 25 | 60 |
| Acetic Acid, Glacial | CR | 100 | 30 |
| Acetic Anhydride | CR | 100 | 35 |
| Acetone | CR | 2 | 70 |
| | CR | 10 | 60 |
| | CR | 100 | 0 |
| Acetonitrile | CR | 20 | 40 |
| | CR | 100 | 0 |
| Acetyl Acetone | CR | 20 | 50 |
| | CR | 100 | 0 |
| Acrolein (Acrylaldehyde) | CR | 20 | 40 |
| | CR | 100 | 0 |
| Acrylamide | CR | 50 | 40 |
| Acrylic Acid | CR | 25 | 40 |
| | CR | 100 | 40 |
| Acrylic Latex | CR | All | 80 |

| | | | |
|--|-----|-----------|-----|
| Acrylonitrile | CR | 20 | 40 |
| | CR | 100 | 0 |
| Acrylonitrile Latex Dispersion | CR | 2 | 25 |
| Activated Carbon Beds,Water Treatment | CR | 100 | 90 |
| Adipic Acid A.S | CR | 100 | 80 |
| Alcohol, Amyl | CR | 100 | 65 |
| Alcohol, Butyl | CR | 100 | 65 |
| Alcohol, Ethyl | CR | 95 | 40 |
| Alcohol, Isodecyl | CR | 100 | 80 |
| Alcohol, Propyl | CR | 100 | 50 |
| Alkyl Aryl Sulfonate Salts | CR | All | 60 |
| Alkyl (C8-C10) Dimethyl Amine | CR | 100 | 100 |
| Alkyl (C8-C18) Chloride | CR | > 0.5 | 100 |
| Alkyl Aryl Ammonium Salt | CR | All | 80 |
| Alkyl Aryl Sulfonic Acid | CR | All | 60 |
| Alkyl Benzene Ammonium Salt | CR | All | 80 |
| Alkyl Benzene Sulfonic Acid | CR | All | 60 |
| Alkyl Phenol Polyglycol Ether Sulfates and | CR | All | 60 |
| Alkyl Sulfonate | CR | All | 60 |
| Alkyl Sulfonic Acid | CR | All | 60 |
| Allyl Alcohol | CR | 100 | 25 |
| Allyl Chloride | CR | 100 | 25 |
| Alpha-Methylstyrene | CR | 100 | 50 |
| Alpha-Oleum Sulfates | CR | 100 | 50 |
| Alum | CR | All | 120 |
| Alumina Hydrate | CR | All | 80 |
| Aluminum Chloride | CR | 100 | 120 |
| Aluminum Chlorohydrate | CR | All | 100 |
| Aluminum Chlorohydroxide | CR | 50 | 95 |
| Aluminum Fluoride | DSV | All | 30 |
| Aluminum Hydroxide | DSV | 100 | 95 |
| Aluminum Nitrate | CR | > 0.5 | 100 |
| | CR | Sat'd | 90 |
| Aluminum Potassium Sulfate | CR | 100 | 120 |
| Aluminum Sulfate | CR | 100 | 120 |
| Aluminum Sulfate Reactor | CR | > 0.5 | 100 |
| AMBITROL Ethylene Glycol | CR | > 0.5 | 100 |
| Amine Salts | CR | All | 65 |
| Amino Acids | CR | All | 45 |
| Ammonia | CR | Liquified | 0 |
| | | Gas | 0 |
| Ammonia Gas | CR | 100 | 40 |
| Ammonia Gas (Dry) | CR | 100 | 40 |
| Ammonia Vapors (Wet) | CR | 40 vol % | 80 |
| Ammonium | CR | 10 | 70 |
| | CR | 50 | 70 |
| Ammonium Acetate | CR | All | 40 |
| Ammonium Bicarbonate | CR | 0.5 - 50 | 70 |
| Ammonium Bicarbonate | CR | Sat'd | 70 |
| Ammonium Bifluoride | CR | All | 65 |
| Ammonium Bisulfite Black Liquor | CR | 100 | 80 |
| Ammonium BisulfiteCooking Liquor | CR | 100 | 65 |
| Ammonium Bromate | CR | All | 80 |
| Ammonium Bromide | CR | All | 80 |

| | | | |
|--|-----|-------------|-----|
| Ammonium Carbonate | CR | All | 70 |
| Ammonium Chloride | CR | > 0.5 | 100 |
| | CR | All | 100 |
| Ammonium Citrate | CR | All | 65 |
| Ammonium Fluoride | DSV | 100 | 65 |
| Ammonium Hydroxide | DSV | 6-20 | 70 |
| | DSV | 0.5 - 5 | 80 |
| Ammonium Hydroxide | DSV | 30 (as NH3) | 40 |
| Ammonium Lauryl Sulfate | CR | All | 50 |
| Ammonium Ligno Sulfonate | CR | All | 80 |
| Ammonium Molybdate | CR | All | 65 |
| Ammonium Nitrate | CR | All | 120 |
| Ammonium Oxalate | CR | All | 65 |
| Ammonium Pentaborate | CR | All | 50 |
| Ammonium Perchlorate | CR | 0.5 - 15 | 75 |
| Ammonium Persulfate | CR | All | 80 |
| Ammonium Phosphate, dibasic | CR | All | 100 |
| Ammonium Phosphate, monobasic | CR | All | 100 |
| Ammonium Polysulfide | CR | All | 65 |
| Ammonium Sulfate | CR | All | 120 |
| Ammonium Sulfide (Bisulfide) | CR | All | 50 |
| Ammonium Sulfite | CR | 100 | 65 |
| Ammonium Thiocyanate | CR | 0.5 - 20 | 100 |
| | CR | 100 | 50 |
| Ammonium Thioglycolate | CR | All | 40 |
| Ammonium Thiosulfate | CR | All | 50 |
| AmmoniumPotassium | CR | All | 100 |
| Amyl Acetate | CR | 100 | 40 |
| | CR | > 0.5 | 50 |
| Amyl Alcohol | CR | 100 | 65 |
| Amyl Alcohol, Vapor | CR | 100 | 100 |
| Amyl Chloride | CR | 100 | 50 |
| Aniline | CR | 20 | 40 |
| Aniline | CR | 100 | 0 |
| Aniline Hydrochloride | CR | All | 80 |
| Aniline Sulfate | CR | All | 100 |
| Animal Fat | CR | 100 | 80 |
| Anionic Surfactant | CR | All | 50 |
| Anthracene oil | CR | 6 | 30 |
| Aqueous Ammonia (See Ammonium Hydroxide) | DSV | 5 | 82 |
| | DSV | 10 | 70 |
| | DSV | 20 | 70 |
| Aqueous Sodium Chloride | CR | All | 100 |
| Arsenic Acid | CR | All | 80 |
| Barium Acetate | CR | All | 80 |
| Barium Bromide | CR | All | 95 |
| Barium Carbonate | CR | All | 120 |
| Barium Chloride | CR | All | 100 |
| Barium Cyanide | CR | All | 65 |
| Barium Hydroxide | CR | All | 65 |
| Barium Sulfate | CR | All | 82 |
| Barium Sulfide | CR | All | 80 |
| Barley Solution | CR | > 0.5 | 75 |

| | | | |
|--|-----|-----------|-----|
| Beer | CR | > 0.5 | 50 |
| Beet Sugar Liquor | CR | > 0.5 | 80 |
| Benzaldehyde | CR | 100 | 0 |
| Benzalkonium Chloride | CR | DILUTE | 40 |
| Benzene | CR | 100 | 40 |
| Benzene Sulfonic Acid | CR | 50 | 65 |
| Benzene, Vapor | CR | 100 | 40 |
| Benzoic Acid | CR | All | 100 |
| Benzoyl chloride | CR | 100 | 25 |
| Benzoyl peroxide | CR | 50 | 25 |
| Benzyl Alcohol | CR | 20 | 50 |
| | CR | 100 | 40 |
| Benzyl benzoate | CR | 100 | 0 |
| Benzyl Chloride | CR | 100 | 25 |
| Benzyl octyle adipate | CR | 100 | 40 |
| BenzyltrimethylammoniumChloride | CR | 60 | 40 |
| Bicarbonate | CR | 50 | 70 |
| Black Liquor Recovery,Furnace Gases | CU | 100 | 205 |
| Black Liquor(Pulp & Kraft Mill) | DSV | Thin | 80 |
| Black Liquor(Pulp & Kraft Mill)Thick,Heavy | DSV | Thick | 105 |
| Bleach (javel water) | CR | 100 | 25 |
| Bleaching Agent | CR | 100 | 0 |
| Borax | CR | All | 100 |
| Boric Acid | CR | All | 100 |
| Boron Trichloride Scrubbing | CR | > 0.5 | 65 |
| Brake Fluids | CR | 100 | 50 |
| Brine | CR | 100 | 0 |
| Brine, Salt | CR | 100 | 120 |
| Brominated Phosphate Ester | CR | > 0.5 | 50 |
| Bromine Dry Gas | CR | All | 40 |
| Bromine Wet Gas | CR | 100 | 40 |
| Bromine, Liquid | CR | 100 | 0 |
| Brown Stock | CR | 100 | 90 |
| Bunker C Fuel Oil (heavy fraction) | CR | 100 | 105 |
| Butadiene (Gas) | CR | 100 | 45 |
| Butane | CR | 100 | 60 |
| Butanediol | CR | 100 | 40 |
| Butanol | CR | 100 | 65 |
| Butyl Acetate | CR | 100 | 30 |
| Butyl Acrylate | CR | 100 | 25 |
| Butyl Alcohol | CR | All | 65 |
| Butyl Alcohol/Benzene | CR | 93/4 | 50 |
| Butyl Amine | CR | 100 | 0 |
| Butyl Benzoate | CR | 70 | 40 |
| Butyl Benzyl Phthalate | CR | 100 | 100 |
| Butyl Carbitol, DiethyleneGlycol Butyl Ether(DOWANOL DB) | CR | 100 | 40 |
| Butyl CELLOSOLVE Solvent(DOWANOL EB) | CR | 100 | 40 |
| Butyl Chloride | CR | 0.1 - 100 | 25 |
| Butyl Hypochlorite | CR | 98 | 0 |
| Butyl Stearate(5% in Mineral Spirits) | CR | All | 40 |
| Butylene Glycol | CR | 100 | 80 |
| Butylene Oxide | CR | 100 | 0 |

| | | | |
|--|------------|-------------|-----|
| Butyraldehyde | CR | 100 | 35 |
| Butyric Acid | CR | 25 | 100 |
| | CR | 50 | 100 |
| | CR | 100 | 45 |
| | CR | 100 | 25 |
| Butyrolactone | CR | 100 | 25 |
| Cadmium Chloride | CR | All | 100 |
| Calcium Bisulfite | CR | All | 100 |
| Calcium Bromide | CR | All | 100 |
| Calcium Carbonate (slurry) | CR | All | 80 |
| Calcium Chlorate | CR | All | 120 |
| Calcium Chloride | CR | All | 120 |
| Calcium Hydroxide | CR | 25 | 100 |
| | CR | 100 | 90 |
| Calcium Hypochlorite | DSV+PC+BPO | All | 80 |
| Calcium Nitrate | CR | All | 100 |
| Calcium Sulfate | CR | All | 120 |
| Calcium Sulfate | CR | All | 120 |
| Calcium Sulfite | CR | All | 100 |
| Calgon (Product E)Sodium Hexametaphosphate | CR | All | 50 |
| Camphor oil | CR | 100 | 25 |
| Cane Sugar Liquor & Sweetwater | CR | All | 80 |
| Capric Acid (Decanoic Acid) | CR | All | 80 |
| Caproic Acid (Hexanoic Acid) | CR | 100 | 50 |
| Caprolactam | CR | 100 | 0 |
| | CR | 0 - 50 | 40 |
| Caprolactone | CR | 100 | 0 |
| Caprylic Acid (Octanoic Acid) | CR | 100 | 100 |
| Caramel | CR | All | 50 |
| Carbon Dioxide Gas | CR | All | 205 |
| Carbon Disulfide | CR | 100 | 0 |
| Carbon Disulfide Fumes,no condensation or coalescence | CR | All | 60 |
| Carbon Monoxide Gas | CR | - | 205 |
| Carbon Tetrachloride | CR | 100 | 80 |
| Carbon Tetrachloride, Vapor | CR | All | 90 |
| CARBOWAX Polyethylene Glycol | CR | 100 | 80 |
| Carboxyethyl Cellulose | CR | 10 | 65 |
| Carboxymethyl Cellulose | CR | All | 65 |
| Cashew Nut Oil | CR | 100 | 65 |
| Castor Oil (Ricinus Oil) | CR | 100 | 70 |
| Cationic/Anionic Polymer Emulsions in Kerosene orPetroleum Distillates/Water | CR | 0 - 50 | 50 |
| Caustic (see Sodium Hydroxide) | CR | 100 | 0 |
| Cetyl Alcohol (Hexadecanol) | CR | 100 | 80 |
| Chlordimeform (Galecron Insecticide) | CR | 100 | 50 |
| Chloric Acid | CR | All | 25 |
| Chlorinated Brine, pH < 2.5 | DSV+PC+BPO | Sat'd Cl2 | 95 |
| Chlorinated Brine, pH > 9 (Hypochlorite) | PBPO - DSV | Sat'd Cl2 | 80 |
| Chlorinated Pulp | CU | All | 95 |
| Chlorinated Wax | CR | All | 80 |
| Chlorination Washer(Hoods & Vent Systems) | CR | Vapors, All | 95 |

| | | | |
|--|---------------------|-------------|-----|
| Chlorine Dioxide | CR DSV | All | 65 |
| Chlorine Dioxide Scrubber | PBPO - DSV | 100 | 75 |
| Chlorine Dioxide, No Chlorine (Bleaching Solution,with or without Pulp) | CU | All | 95 |
| Chlorine Dioxide,Solution Storage | CR | 100 | 20 |
| Chlorine Dry Gas | CR DVC | 100 | 120 |
| Chlorine Water, pH < 2.5 | CR | Sat'd Cl2 | 95 |
| Chlorine Water, pH > 9(Hypochlorite) | PBPO - DSV CR | Sat'd Cl2 | 80 |
| Chlorine Water, pH 2.5-9 | CU CR | Sat'd Cl2 | 0 |
| Chlorine, Wet Gas | DSV-AC CR | 100 | 120 |
| Chlorine-Hydrogen Chloride, with AqueousCondensate | DSV-AC -DVC- ACR | 8 - 10% HCl | 100 |
| Chloroacetic Acid | CR | 0 - 25 | 50 |
| | CR | 26 - 50 | 40 |
| | CR | 51 - 79 | 30 |
| | CR | 80 - 85 | 25 |
| | CR | 86 - 100 | 0 |
| Chlorobenzene | CR | 100 | 40 |
| Chloroform | CR | 100 | 0 |
| Chloroform, Fumes,No Condensation or Coalescence | CR | Fumes | 80 |
| Chloropentane (1 to 5 Cl) | CR | 100 | 55 |
| Chloropicrin (Nitrochloroform) | CR | 100 | 0 |
| Chloropropionic acid | CR | 100 | 25 |
| Chloropyridine (tetra) | CR | 100 | 50 |
| Chlorosulfonic Acid | CR | 10 | 0 |
| CHLOROTHENE SM(1,1,1- Trichloroethane inhibited) | CR | 100 | 50 |
| Chlorotoluene | CR | 100 | 40 |
| Choline Chloride | CR | All | 65 |
| Chrome Reduction Process | CU | 25 | 90 |
| Chromic Acid | CR+PC | 5 | 65 |
| | CR+PC | 10 | 65 |
| | CR+PC | 20 | 50 |
| | CR+PC | 30 | 0 |
| Chromic/Sulphuric Acid | CR+PC | 10 | 0 |
| Chromium Plate, Electroplating with a Salt Solution (withSulfuric Acid: Not Recommended) | CR | 100 | 55 |
| Chromium Sulfate(water soluble forms) | CR | All | 100 |
| Citric Acid | CR | All | 100 |
| Clopidol (Coyden) | CCSR | All | 40 |
| Cobalt Chloride | CR | All | 100 |
| Cobalt Citrate | CR | All | 80 |
| Cobalt Nitrate | CR | All | 100 |
| Coconut Oil | CR | 100 | 95 |
| Cod-liver Oil | CR | 100 | 40 |
| Copper Chloride | CR | All | 105 |
| Copper Cyanide | CR | All | 100 |
| Copper Nitrate | CR | All | 100 |
| Copper oxychloride | CR | 20 | 60 |

| | | | |
|--|------|--------|-----|
| Copper Sulfate | CR | All | 120 |
| Corn Oil | CR | 100 | 100 |
| Corn Starch | CR | Slurry | 100 |
| Corn Sugar/Syrup (Glucose) | CR | All | 100 |
| Cottonseed Oil | CR | 100 | 100 |
| Cresol A.S | CR | 1 | 25 |
| Crotonaldehyde | CR | 100 | 0 |
| Crude Oil, Sweet, Sour | CR | 100 | 120 |
| Cumene | CR | 100 | 50 |
| Cyanuric Acid | CR | All | 50 |
| Cyanuric Chloride | CCSR | All | 50 |
| Cyclohexane | CR | 100 | 65 |
| Cyclohexanol | CR | 100 | 35 |
| Cyclohexylamine | CR | 100 | 30 |
| Cyclopentane | CR | 100 | 50 |
| D.D.T | CR | 2.50% | 60 |
| Dalapon Grass Killer(2,2-dichloropropionic acid and sodium salt) | CR | 100 | 40 |
| Decanoic Acid | CCSR | All | 80 |
| Decanol | CR | 100 | 80 |
| Deionized Water | CR | 100 | 80 |
| Demineralized Water | CR | 100 | 80 |
| Detergents, Organic | CR | 100 | 95 |
| De-waxed Paraffin Distillate | CR | 100 | 80 |
| Dextrin A.S | CR | 100 | 25 |
| Di-(2-ethylhexyl)adipate | CR | 100 | 50 |
| Di-2-Ethylhexyl Phosphoric Acid(DEHPA) in Kerosene | CR | 20 | 80 |
| Diacetone Alcohol | CR | 10 | 50 |
| | CR | 100 | 0 |
| Diallyl Phthalate | CR | All | 100 |
| Diammonium Phosphate | CR | All | 100 |
| Dibromonitrilo-Propionamide | CR | 100 | 40 |
| Dibromophenol | CR | 100 | 40 |
| Dibromopropane | CR | 100 | 40 |
| Dibromopropanol | CR | 100 | 40 |
| Dibutyl Carbitol (diethyleneglycol dibutyl ether) | CR | 100 | 40 |
| Dibutyl Ether | CR | 100 | 65 |
| Dibutyl phosphate | CR | 100 | 60 |
| Dibutyl Phthalate | CR | 100 | 100 |
| Dibutyl Sebacate | CR | 100 | 65 |
| Dichloro-1,4 butane | CR | 100 | 0 |
| Dichlorobenzene(o-, m-, p-) | CR | 100 | 50 |
| Dichlorobenzene(ortho and para) | CR | 100 | 50 |
| Dichloroethane | CR | 100 | 25 |
| Dichloroethylene | CR | 100 | 0 |
| Dichloromethane (Methylene Chloride) | CR | 100 | 0 |
| Dichloropropane | CR | 100 | 40 |
| Dichloropropene | CR | 100 | 25 |
| Dichloropropionic Acid(see also Dalapon) | CR | 100 | 40 |
| Dichlorotoluene | CR | 100 | 50 |
| Diesel Engine Oil | CR | 100 | 100 |

| | | | |
|--|----|-------|-----|
| Diesel Fuel | CR | 100 | 90 |
| Diethanolamine | CR | 100 | 65 |
| Diethyl Benzene | CR | 100 | 65 |
| Diethyl Carbonate | CR | 100 | 40 |
| Diethyl Ether | CR | 100 | 0 |
| Diethyl Formamide | CR | 20 | 40 |
| | CR | 100 | 0 |
| Diethyl Hydroxylamine | CR | 100 | 0 |
| Diethyl Ketone | CR | 20 | 50 |
| | CR | 100 | 0 |
| Diethyl Sulfate | CR | 100 | 50 |
| Diethylamine | CR | 20 | 40 |
| | CR | 100 | 0 |
| Diethylaminoethanol | CR | 100 | 50 |
| Diethylbenzene | CR | 100 | 65 |
| Diethylene Glycol | CR | All | 100 |
| Diethylene Glycol Dimethylether | CR | 20 | 40 |
| | CR | 100 | 0 |
| Diethylenetriaminepentaacetic Acid | CR | All | 50 |
| Diethylenetriaminepentaacetic Acid,sodium salt | CR | 40 | 50 |
| Di-ethyl-ether | CR | 100 | 0 |
| Diethylphthalate | CR | 100 | 60 |
| Diglycolamine (Aminoethoxyethanol) | CR | 20 | 50 |
| | CR | 50 | 40 |
| | CR | 100 | 0 |
| Diisobutyl Ketone | CR | 100 | 50 |
| Diisobutyl Phthalate | CR | 100 | 65 |
| Diisobutylene | CR | 100 | 40 |
| Diisonoyl Phthalate | CR | 100 | 100 |
| Diisopropanolamine | CR | 100 | 65 |
| Diisopropylamine | CR | 100 | 25 |
| Dimethyl Acetamide | CR | 20 | 40 |
| | CR | 100 | 0 |
| Dimethyl Acetamide, Fumes,no condensation orcoalescence | CR | Fumes | 80 |
| Dimethyl Amine | CR | 20 | 40 |
| | CR | 40 | 0 |
| Dimethyl Aniline | CR | 100 | 40 |
| Dimethyl Formamide | CR | 20 | 40 |
| | CR | 100 | 0 |
| Dimethyl Formamide, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Dimethyl Morpholine | CR | 100 | 40 |
| Dimethyl Phthalate | CR | 100 | 80 |
| Dimethyl Sulfate | CR | 20 | 50 |
| | CR | 100 | 0 |
| Dimethyl Sulfide | CR | 100 | 25 |
| Dimethyl Sulfoxide | CR | 20 | 40 |
| | CR | 100 | 0 |
| Dimethyl Sulfoxide (DMSO) - Water Solution | CR | 20 | 20 |
| Dimethylamine | CR | 100 | 25 |

| | | | |
|--|----|-----|-----|
| Dimethylammonium Hydrochloride (Dimethylamine HCl, DMA-HCl) | CR | 70 | 50 |
| Dimethylcarbonate | CR | 100 | 0 |
| Dimethylphthalate | CR | 100 | 60 |
| Dimethylsulphate | CR | 100 | 25 |
| Di-n-butylamine | CR | 100 | 25 |
| Diocetyl Phthalate | CR | 100 | 100 |
| Dioxanne | CR | 100 | 0 |
| Diphenyl Oxide (Diphenyl Ether, Phenyl Ether) | CR | 100 | 50 |
| Dipotassium Phosphate | CR | All | 100 |
| Dipropylene Glycol | CR | All | 100 |
| Dipropylene Glycol Monomethyl Ether | CR | 20 | 65 |
| (DOWANOL DPM) | CR | 100 | 20 |
| Disodium tetraborate A.S | CR | 100 | 90 |
| Distilled Water | CR | 100 | 80 |
| Divinyl Benzene | CR | 100 | 50 |
| DMA 4 Weed Killer 2,4-D | CR | 100 | 50 |
| DMA 6 Weed Killer | CR | 100 | 50 |
| Dodecanol (Lauryl Alcohol) | CR | 100 | 80 |
| Dodecene | CR | 100 | 80 |
| Dodecyl Benzene Sulfonic Acid | CU | 100 | 100 |
| Dodecyldimethylamine | CR | 100 | 100 |
| Dodecylmercaptan | CR | 100 | 100 |
| DOW THERM | CR | 100 | 65 |
| DOWANOL DB Diethylene Glycol n-Butyl Ether (see also Butyl CARBITOL) | CR | 100 | 40 |
| DOWANOL DB Glycol Ether | CR | 100 | 40 |
| DOWANOL DPM (Dipropylene | CR | 100 | 0 |
| DOWANOL EB Glycol Ether (Ethylene Glycol n-butyl ether) | CR | 100 | 40 |
| DOWANOL PM Glycol Ether | CR | 100 | 20 |
| DOWANOL PM Glycol Ether Glycol Monomethyl Ether) | CR | 100 | 20 |
| DOWCLENESolvent | CR | 100 | 50 |
| DOWCLENES* EC Solvent | CR | 100 | 50 |
| DOWEX 50WX4 Ion Exchange Resin | CR | 100 | 100 |
| DOWFAX 2A1 Surfactant | CR | All | 50 |
| DOWFAX 2AO Solution Surfactant | CR | All | 50 |
| DOWICIDE Antimicrobial | CR | All | 50 |
| DOWTHERM* Heat Transfer Agent | CR | 100 | 65 |
| Electrosol™ Antistatic Agent (Petroleum naphtha, heavy alkylate) | CR | All | 65 |
| Epichlorohydrin | CR | 100 | 25 |
| Epoxidized Castor Oil | CR | 100 | 40 |
| Epoxidized Soybean Oil | CR | 100 | 65 |
| Epoxy resin | CR | 100 | 25 |
| Essential oil | CR | 100 | 25 |
| Esters, Fatty Acid | CR | 100 | 80 |
| Ethanol (Ethyl Alcohol) | CR | 10 | 65 |
| | CR | 50 | 60 |
| | CR | 100 | 0 |

| | | | |
|--|----|---------|-----|
| | CR | 90 - 95 | 40 |
| Ethanol A.S | CR | 50 | 40 |
| Ethanol, Fumes, no condensation or coalescence | CR | Fumes | 80 |
| Ethanalamine | CR | 20 | 50 |
| | CR | 100 | 40 |
| Ethephon | CR | 100 | 40 |
| Ethoxy Acetic Acid | CR | 10 | 40 |
| | CR | 100 | 0 |
| Ethoxylated Alcohol, C12-C14 | CR | 100 | 50 |
| Ethoxylated Nonyl Phenol | CR | 100 | 40 |
| Ethyl Acetate | CR | 100 | 25 |
| Ethyl Acetate, Fumes, no condensation or coalescence | CR | Fumes | 80 |
| Ethyl Acrylate | CR | 100 | 25 |
| Ethyl Alcohol | CR | 50 | 60 |
| Ethyl Amine | CR | 20 | 40 |
| | CR | 40 | 25 |
| | CR | 70 | 0 |
| Ethyl Bromide | CR | 100 | 0 |
| Ethyl Chloride | CR | 100 | 25 |
| Ethyl Ether | CR | 100 | 0 |
| Ethyl Sulfate | CR | 100 | 40 |
| Ethyl-3-Ethoxy Propionate | CR | 100 | 25 |
| Ethylamine | CR | 35 | 25 |
| Ethylbenzene | CR | 100 | 50 |
| Ethylene Chloride(see Dichloroethane) | CR | 100 | 25 |
| Ethylene Chlorohydrin | CR | 20 | 65 |
| | CR | 100 | 40 |
| Ethylene Diamine | CR | 20 | 40 |
| | CR | 100 | 0 |
| Ethylene Dibromide | CR | 100 | 0 |
| Ethylene Dichloride(see Dichloroethane) | CR | 100 | 25 |
| Ethylene Glycol | CR | 100 | 100 |
| Ethylene glycol acetate | CR | 100 | 25 |
| Ethylene Glycol Monobutyl | CR | 20 | 65 |
| Ether(DOWANOL EB) | CR | 100 | 40 |
| Ethylene Oxide | CR | 100 | 0 |
| Ethylenediaminetetraacetic Acid(EDTA)) | CR | All | 80 |
| Ethylenesulfonic Acid,Sodium Salt | CU | All | 70 |
| EthyleneTetraChloride | CR | 100 | 50 |
| Ethylhexanol | CR | 100 | 40 |
| Eucalyptus Oil | CR | 100 | 60 |
| Fatty Acid/Sterol/Triglyceride | CR | All | 120 |
| Fatty Acid/Sulfuric Acid | CR | 5 | 100 |
| Fatty Acids | CR | All | 120 |
| Ferric Acetate | CR | All | 80 |
| Ferric Chloride | CR | All | 100 |
| Ferric Chloride/Ferrous Chloride | CR | 5-20 | 100 |
| Ferric Sulfate | CR | All | 100 |
| Ferrous Chloride | CR | All | 100 |
| Ferrous Nitrate | CR | All | 100 |

| | | | |
|---|--------|----------|-----|
| Ferrous Sulfate | CR | All | 100 |
| Flue Gas, Dry | CR | All | 200 |
| Flue Gas, Wet | CR DSV | All | 100 |
| Fluoboric Acid | DSV+PC | 10 | 100 |
| | DSV+PC | 25 | 60 |
| Fluorine in Flue Gas, Wet | DSV+PC | 2 | 100 |
| Fluosilicic Acid | DSV+PC | 10 | 80 |
| | DSV+PC | 25 | 35 |
| | DSV+PC | 35 | 35 |
| Fluosilicic Acid Fumes | DSV | All | 80 |
| Fly Ash Slurry | CR | 100 | 80 |
| Formaldehyde | CR | All | 65 |
| Formaldehyde A.S | CR | 25 | 60 |
| | CR | 35 | 50 |
| Formamide | CR | 20 | 65 |
| | CR | 100 | 20 |
| Formic Acid | CR | 30 | 80 |
| | CR | 50 | 50 |
| Fruit juice | CR | 100 | 25 |
| Fuel Oil | CR | 100 | 100 |
| Furfural | CR | 100 | 0 |
| | LOS | 0 - 10 | 50 |
| Furfural in Organic Solvent | CCSR | 0 - 20 | 40 |
| Furfural in Water | CR | 5 | 50 |
| Furfuryl Alcohol | CR | 20 | 65 |
| | CR | 100 | 25 |
| Galecron (Chlordimeform)Insecticide 100 | CR | 100 | 50 |
| Gallic Acid | CR | All | 80 |
| Gasohol (10-100% Alcohol) | CR | 100 | 40 |
| Gasohol (5% Methanol) | CR | 100 | 50 |
| Gasohol (Up to 10% Alcohol) | CR | 100 | 50 |
| Gasoline | CR | 100 | 50 |
| Gasoline (5% Methanol) | CR | 100 | 50 |
| Gasoline (Up to 10% Alcohol) | CR | 100 | 50 |
| Gasoline, Aviation | CR | 100 | 65 |
| Gasoline, Leaded | CR | 100 | 65 |
| Gasoline, No Lead, No Methanol | CR | 100 | 65 |
| Glucose | CR | 100 | 100 |
| Glutamic Acid | CR | 50 | 50 |
| Glutaraldehyde | CR | 50 | 50 |
| Glutaric Acid | CR | All | 50 |
| Glycerine | CR | 100 | 100 |
| Glycerol | CR | 75 | 90 |
| Glycerol triacetate | CR | 100 | 25 |
| Glycine and Derivatives | CR | All | 40 |
| Glycol | CR | 100 | 100 |
| Glycolic Acid | CR | 30 | 65 |
| | CR | 0.5 - 10 | 65 |
| | CR | 70 | 40 |
| Glyconic Acid | CR | 50 | 80 |
| Glyoxal | CR | 40 | 40 |
| Glyphosate | CR | All | 40 |
| Goodrite K702/732 Product(Sodium Polyacrylate Disperants) | CR | 100 | 80 |
| Grease | CR | 100 | 90 |

| | | | |
|--|---------------------|-------------|-----|
| Green Liquor | DSV | All | 80 |
| Green liquor (Pulp Mill) | CR | All | 80 |
| Gypsum Slurry | CR | All | 100 |
| Gypsum Slurry (see also Calcium Sulfate) | CR | All | 100 |
| Hard Chrome Plating Baths (with Sulfuric Acid: Not Recommended) | CR | 100 | 60 |
| Heptane | CR | 100 | 100 |
| Heptane, Fumes, no condensation or coalescence | CR | Fumes | 80 |
| Hexachloroethane | CR | 100 | 50 |
| Hexadecanol | CR | 100 | 80 |
| Hexamethylenetetramine | CR | 40 | 50 |
| Hexane | CR | 100 | 70 |
| Hexanoic Acid | CR | 100 | 50 |
| Hydrazine | CR | 20 | 0 |
| | CR | 100 | 0 |
| Hydrazinium hydroxide | CR | 20 | 25 |
| Hydriodic Acid | CR | 40 | 65 |
| | CR | 50 | 40 |
| | CR | 57 | 40 |
| Hydrobromic Acid | CR | 25 | 80 |
| | CR | 48 | 65 |
| | CR | 62 | 40 |
| | CR | 0 - 25 | 80 |
| Hydrochloric Acid | DSV AC -DVC-ARV-CCP | 37 | 50 |
| | DSV AC -DVC-ARV-CCP | 31 - 32 | 80 |
| | DSV AC -DVC-ARV-CCP | 33 - 34 | 70 |
| | DSV AC -DVC-ARV-CCP | 35 - 36 | 60 |
| | DVC+ECR+CC | 10 | 100 |
| | DVC+ECR+CC | 20 | 100 |
| | DVC+ECR+CC | 25 | 95 |
| Hydrochloric Acid | DVC+ECR+CC | 30 | 80 |
| | DVC+ECR+CC | 36 | 60 |
| Hydrochloric Acid and trace organics | DVC+ECR+CC | 0 - 33% HCl | 60 |
| Hydrochloric Acid, Fumes | DVC+ECR+CC | 100 | 130 |
| Hydrocyanic Acid | CR | 10 | 80 |
| Hydrocyanic Acid | CR | All | 100 |
| Hydrofluoric acid A.S (no glass on surface ,no thixotropic resin) | DSV+PC | 10 | 65 |
| | DSV+PC | 15 | 40 |
| | DSV+PC | 20 | 30 |
| Hydrogen Bromide, Dry Gas | CR | 100 | 80 |
| Hydrogen Bromide, Wet Gas | CR | 100 | 80 |
| Hydrogen Chloride dry Gas | DVC+ECR+CC | 100 | 170 |
| Hydrogen Chloride wet Gas | DVC+ECR+CC | 100 | 170 |
| Hydrogen Fluoride, Dry Gas/Vapor (if wet max. 40°C) | CU-PBPO - DSV | 100 | 80 |
| Hydrogen gas | CR | 100 | 60 |
| | CU-PBPO | 35 | 40 |

| | | | |
|---|------------|----------|-----|
| Hydrogen Peroxide | DSV+PC+BPO | 30 | 65 |
| | DSV+PC+BPO | 35 | 40 |
| | DSV+PC+BPO | 50 | 0 |
| Hydrogen Sulfide | CU | 5 | 150 |
| Hydrogen Sulfide, Aqueous | CR | All | 100 |
| Hydrogen Sulfide, Dry Gas | CR | 100 | 110 |
| Hydroxyacetic Acid(Glycolic Acid) | CR | 20 | 65 |
| | CR | 70 | 40 |
| Hypochlorous Acid | CR | 20 | 65 |
| | CR | 10 | 82 |
| | PBBO | 0 - 10 | 40 |
| Hypophosphorous Acid | CR | 0 - 50 | 50 |
| Iodine, Crystals | CR | 100 | 65 |
| Iodine, Vapor | CR | 100 | 80 |
| Iron chloride A.S | CR | 25 | 60 |
| | CR | 100 | 60 |
| Isoamyl acetate | CR | 100 | 25 |
| Isoamyl Alcohol | CR | 20 | 80 |
| | CR | 100 | 65 |
| Isobutyl Alcohol | CR | 20 | 80 |
| | CR | 100 | 65 |
| Isodecanol | CR | 100 | 80 |
| isodecyl Alcohol | CR | 100 | 80 |
| Isononyl Alcohol | CR | 100 | 65 |
| Isooctyl Adipate | CR | 100 | 65 |
| Isooctyl Alcohol | CR | 100 | 65 |
| Isopropanol | CR | 100 | 60 |
| Isopropanol Amine | CR | 100 | 50 |
| Isopropyl Alcohol | CR | All | 50 |
| Isopropyl Amine | CR | 100 | 0 |
| | CR | 0.5 - 50 | 40 |
| Isopropyl Myristate | CR | 100 | 110 |
| Isopropyl Palmitate | CR | 100 | 110 |
| Isopropylamine | CR | 50 | 25 |
| Itaconic Acid | CR | 0.5 - 40 | 60 |
| Jet Fuel, General | CR | 100 | 60 |
| Kerosene | CR | 100 | 80 |
| Kraft Recovery Boiler Breaching(see Flue Gas) | CR | 100 | 0 |
| Labarraque's solution | CR | 100 | 25 |
| Lactic Acid | CR | All | 100 |
| Lactic acid A.S | CR | 10 | 90 |
| | CR | 80 | 60 |
| Lasso Herbicide | CCSR | All | 50 |
| Latex (Emulsion in Water)(for specific latices see under chemical/polymer name) | CR | All | 50 |
| Latex dispersion (60 %) | CR | 100 | 25 |
| Latex, Paint Emulsion | CR | All | 50 |
| Lauroyl Chloride | CR | 100 | 50 |
| Lauryl Alcohol | CR | 100 | 80 |
| Lauryl Chloride | CR | 100 | 100 |
| Lauryl Mercaptan | CR | 100 | 100 |
| Lead Acetate | CR | 100 | 110 |
| Levulinic Acid | CR | 100 | 110 |

| | | | |
|--|------------|---------------|-----|
| Lignin Sulfonate | CR | All | 80 |
| Lime Slurry (see Calcium Hydroxide) | CR | 100 | 0 |
| Limestone Slurry(see Calcium Carbonate) | CR | All | 80 |
| Linseed Oil | CR | 100 | 110 |
| Liquid Petroleum Gas (LPG) | CR | 100 | 60 |
| Liquid soap | CR | 100 | 60 |
| Liquid Sugar | CR | All | 100 |
| Lithium Bromide | CR | 100 | 120 |
| Lithium Carbonate | DSV | All | 80 |
| Lithium Chloride | CR | All | 100 |
| Lithium Hydroxide | DSV | All | 80 |
| Lithium Hypochlorite | PBPO - DSV | All | 80 |
| Lubricating oil | CR | 100 | 80 |
| Machine oil | CR | 100 | 25 |
| Magnesium Bisulfite | CR | All | 100 |
| Magnesium Carbonate | CR | All | 100 |
| Magnesium Chloride | CR | All | 120 |
| Magnesium Fluosilicate | DSV | All | 80 |
| Magnesium Hydroxide | DSV | All | 100 |
| Magnesium Nitrate | CR | All | 100 |
| Magnesium Oxide/Lime | CR | 0.1 - 10 | 100 |
| Magnesium Phosphate | CR | > 0.5 | 100 |
| Magnesium Sulfate | CR | All | 120 |
| Magnesium Sulfate,Phosphoric Acid | CR | 1 - 40/0 - 36 | 100 |
| Magnifloc 500 SeriesProducts | CR | All | 60 |
| Magnifloc 837A Products | CR | All | 65 |
| Maleic Acid | CR | > 0.5 | 100 |
| Maleic Acid | CR | All | 100 |
| Manganese Chloride(Manganous Chloride) | CR | All | 100 |
| Manganese Nitrate (Manganous) | CR | All | 100 |
| Margarin | CR | 100 | 25 |
| Melamine | CR | 100 | 25 |
| Melamine Formaldehyde Resin | CR | All | 50 |
| Mercaptoacetic Acid | CR | All | 40 |
| Mercaptoethanol | CR | 10 | 80 |
| Mercuric Chloride | CR | All | 100 |
| Mercurous Chloride | CR | All | 100 |
| Mercury | CR | 100 | 120 |
| Methacrylic Acid | CR | 25 | 50 |
| | CR | 40 | 50 |
| | CR | 100 | 40 |
| Methane Sulfonic Acid | CR | All | 40 |
| Methanol (Methyl Alcohol) | CR | 5 | 50 |
| | CR | 20 | 40 |
| | CR | 40 - 100 | 0 |
| Methanol, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Methyl Acetate | CR | 20 | 0 |
| | CR | 100 | 0 |
| Methyl Alcohol | CR | All | 20 |
| Methyl Bromide | CR | 10 | 25 |
| | CR | 100 | 0 |

| | | | |
|--|--------|---------|-----|
| Methyl Butyl Ketone (MBK),includes Methyl t-Butyl Ketone(MTBK) and other Isomers | CR | 100 | 50 |
| Methyl Chloride, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Methyl Chloride, Gas | CR | All | 65 |
| Methyl Ethyl Ketone | CR | 20 | 40 |
| | CR | 100 | 0 |
| Methyl Formate | CR | 5 | 50 |
| Methyl Isobutyl Ketone (MIBK) | CR | 100 | 50 |
| Methyl Mercaptan (Gas) | CR | All | 65 |
| Methyl Methacrylate | CR | All | 25 |
| Methyl t-Butyl Ether | CR | 100 | 25 |
| Methylamine | CR | 20 | 40 |
| | CR | 40 | 0 |
| | CR | 100 | 0 |
| Methyldiethanolamine | CR | 20 | 80 |
| | CR | 100 | 65 |
| Methylene Chloride | CR | 100 | 0 |
| Methylene Chloride, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Methylmethacrylate | CR | 100 | 0 |
| Methylstyrene (alpha) | CR | 100 | 50 |
| Milk | CR | 100 | 25 |
| Mineral Oils, Aliphatic | CR | 100 | 120 |
| Mineral Spirit | CR | 100 | 120 |
| Molasses | CR | 100 | 80 |
| Monochlorobenzene | CR | 100 | 40 |
| Monomethylhydrazine | CR | 100 | 0 |
| Morpholine | CR | 20 | 50 |
| | CR | 100 | 0 |
| Motor Oil | CR | 100 | 120 |
| Muriatic Acid(see Hydrochloric Acid) | CR | 100 | 0 |
| Myristic Acid | CR | 100 | 120 |
| Naphtha | CR | 100 | 100 |
| Naphtha, Aliphatic | CR | 100 | 100 |
| Naphtha, Aromatic | CR | 100 | 50 |
| Naphtha, Heavy Aromatic | CR | 100 | 50 |
| Naphthalene | CR | 100 | 100 |
| N-butylamine | CR | 50 | 25 |
| N-Chloro-o-Tolyl(Insecticide Emulsion) | CR | 10 | 50 |
| Neopentyl Glycol | CR | 100 | 80 |
| Neutralizer & Desmut | CR | All | 65 |
| Nickel Chloride | CR | All | 100 |
| Nickel Nitrate | CR | All | 100 |
| Nickel Sulfamate | CR | All | 80 |
| Nickel Sulfate | CR | All | 100 |
| Nitric Acid | DSV+PC | 5 | 80 |
| | DSV+PC | 10 | 65 |
| | DSV+PC | 20 | 65 |
| | DSV+PC | 21 - 29 | 50 |
| | DSV+PC | 30 | 40 |
| | DSV+PC | 40 | 30 |
| | DSV+PC | 70 | 0 |

| | | | |
|--|---------------|--------|-----|
| Nitric Acid Fumes,no condensation | DSV+PC | Fumes | 80 |
| Nitric acid vapour | CR | 5 | 60 |
| Nitrobenzene | CR | 100 | 40 |
| Nitrophenol | LOS | 100 | 40 |
| N-methyl-2-pyrrolidone | CR | 10 | 0 |
| | CR | 100 | 0 |
| N-propylamine | CR | 50 | 25 |
| o-Benzoyl Benzoic Acid | CR | All | 100 |
| Octane | CR | 100 | 25 |
| Octanoic Acid | CR | 100 | 100 |
| Oil with methanol and aromatic hydrocarbons. | CR | 100 | 0 |
| Oil, Sweet and Sour, Crude | CR | 100 | 120 |
| Oleic Acid | CR | All | 90 |
| Oleum (Fuming Sulfuric) | CR | 100 | 0 |
| Olive Oils | CR | 100 | 100 |
| Organic detergent (pH8-10-11) | CR | 100 | 60 |
| Oxalic Acid | CR | All | 50 |
| Ozone | CR | 100 | 25 |
| Ozone Gas | CR | 2 | 0 |
| Ozone in solution | CU | 2 mg/L | 40 |
| Palmitic Acid | CR | 100 | 100 |
| Paraffin oil | CR | 100 | 90 |
| Paraffin wax | CR | All | 95 |
| Peanut Oil | CR | All | 95 |
| Pentabromo Diphenyl Oxide | CR | 100 | 50 |
| Pentachlorophenol | CCSR | All | 50 |
| Pentan-1-ol | CR | 100 | 60 |
| Peracetic Acid | CR | 35 | 0 |
| | CU-PBPO - DSV | 20 | 40 |
| Perchloroethylene | CR | 100 | 50 |
| Perchloroethylene vapor | CR | 100 | 50 |
| Perchloric Acid | CR | 10 | 65 |
| Perchloric Acid | CR | 30 | 40 |
| Perchloroethylene | CR | 100 | 50 |
| Petroleum crude | CR | 100 | 50 |
| Phenol (Carbolic Acid) | CR | 5 | 50 |
| Phenol (Carbolic Acid) | CR | 0 - 2 | 50 |
| | CR | 10 | 50 |
| | CR | 15 | 0 |
| | CR | 88 | 0 |
| Phenol A.S | CR | 1 | 25 |
| Phenol Formaldehyde Resin | CR | All | 50 |
| Phenol Sulfonic Acid | CU | All | 25 |
| Phosphoric Acid | CR | All | 100 |
| Phosphoric Acid, Vapor | CU | All | 120 |
| Phosphorous Acid | CR | 70 | 80 |
| Phosphorus Oxychloride | CR | 100 | 0 |
| Phthalate esters | CR | 100 | 60 |
| Phthalic Acid | CCSR | All | 100 |
| Phthalic anhydride | CR | 100 | 105 |
| Picric Acid (Alcoholic) | CCSR | 10 | 45 |
| Pine Oil | CR | 100 | 90 |
| Plating Chemicals | CU | 100 | 0 |
| Plating Solutions, Chrome | DSV+TC | | 60 |

| | | | |
|--|--------|----------|-----|
| Plating Solutions, Copper | DSV+TC | | 50 |
| Plating Solutions, Gold | DSV+TC | | 90 |
| Plating Solutions, Lead | DSV+TC | | 90 |
| Plating Solutions, Nickel | DSV+TC | | 100 |
| Plating Solutions, Zinc | DSV+TC | | 70 |
| Polyacrylamide | CR | All | 80 |
| Polyacrylic Acid | CR | All | 80 |
| Polyester resins | CR | 100 | 25 |
| Polyethyleneimine | CR | All | 80 |
| Polyvinyl Acetate Adhesives | CR | All | 50 |
| Polyvinyl Alcohol | CR | 100 | 80 |
| Polyvinyl Chloride Latex with 35 parts Diocetylphthalate | CR | All | 50 |
| Polyvinyl joiner's glue | CR | 100 | 90 |
| Pot. Permanganate | CR | All | 100 |
| Potassium | CR | 10 | 65 |
| Potassium Aluminum Sulfate | CR | 100 | 120 |
| Potassium Bicarbonate | CR | 10 | 65 |
| | CR | 50 | 82 |
| Potassium Bromide | CR | All | 100 |
| Potassium Carbonate | CR | 10 | 65 |
| | CR | 25 | 65 |
| | CR | 50 | 82 |
| Potassium Chloride | CR | All | 100 |
| Potassium cyanide | CR | 100 | 80 |
| Potassium Dichromate | CR | All | 100 |
| Potassium Ferricyanide | CR | All | 100 |
| Potassium Fluoride | CR | All | 80 |
| Potassium Gold Cyanide | CR | 12 | 100 |
| Potassium hexacyanoferrate | CR | 100 | 90 |
| Potassium hydrogencarbonate | CR | 10-100 % | 60 |
| Potassium Hydroxide | CR | 10 | 65 |
| | CR | 25 | 65 |
| | DSV+PC | 45 | 82 |
| Potassium Iodide | CR | All | 65 |
| Potassium Nitrate | CR | All | 100 |
| Potassium Oxalate | CR | All | 65 |
| Potassium Permanganate | CR | All | 100 |
| Potassium peroxodisulfate | CR | 100 | 25 |
| Potassium Persulfate | CR | All | 100 |
| Potassium Pyrophosphate | CR | 60 | 65 |
| Potassium silicate | CR | 100 | 60 |
| Potassium Silicofluoride | DSV | All | 40 |
| Potassium Sulfate | CR | All | 100 |
| Propane | CR | 100 | 60 |
| Propane-1,2 diol | CR | 100 | 25 |
| Propanol (n-) | CR | 100 | 50 |
| Propanol (n-), Fumes, no condensation or coalescence | CR | Fumes | 80 |
| Propionaldehyde | CR | 100 | 0 |
| Propionic Acid | CR | 100 | 40 |
| | CR | 0 - 50 | 80 |
| Propionyl Chloride | CR | 100 | 0 |
| Propyl Acetate | CR | 100 | 25 |
| Propyl Alcohol | CR | 100 | 50 |
| Propyl Bromide | CR | 100 | 25 |

| | | | |
|---|-----|-------|-----|
| Propyl Chloride | CR | 100 | 25 |
| Propylene Glycol | CR | All | 100 |
| Propylene Glycol Monomethyl Ether | CR | 20 | 50 |
| Acetate(DOWANOL PMA) | CR | 100 | 20 |
| Propylene Oxide | CR | 100 | 0 |
| Propylene Oxide, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Pulp Paper Mill Blow | | | 0 |
| Down(Noncondensable Gases,see also Blow Down) | CR | 100 | 0 |
| Pyridine | CR | 20 | 40 |
| | CR | 100 | 0 |
| Quaternary Amine Salts | CR | All | 80 |
| Quinoline | CR | 20 | 40 |
| | CR | 100 | 0 |
| Rayon Spin Bath | CR | 100 | 60 |
| Rayon Spin Bath | CR | Fumes | 60 |
| Rayon Spinning | CR | Fumes | 60 |
| Red Liquor | CR | All | 80 |
| Rhodoviol | CR | 100 | 40 |
| Salicylaldehyde | CR | 100 | 25 |
| Salicylic Acid | CR | All | 90 |
| Salt Brine | CR | 100 | 120 |
| Salt solutions | CR | 100 | 90 |
| Saturated Aqueous Chlorine | CR | All | 100 |
| Sea Water | CR | 100 | 100 |
| Selenious Acid | CR | All | 100 |
| Silicon Tetrafluoride/Hydrofluoric/ | CR | 100 | 0 |
| Silicone (grease-oil) | CR | 100 | 90 |
| Silver Nitrate | CR | All | 100 |
| Sodium Acetate | CR | > 0.5 | 100 |
| Sodium Alkyd Aryl Sulfonates | CR | All | 80 |
| Sodium Aluminate | DSV | All | 70 |
| Sodium Benzoate | CR | All | 80 |
| Sodium Bicarbonate | CR | All | 80 |
| Sodium Bifluoride | DSV | All | 50 |
| Sodium Bisulfate | CR | All | 100 |
| Sodium Bisulfide (Hydrosulfide) | CR | All | 80 |
| Sodium Borate | CR | > 0.5 | 100 |
| Sodium Borohydride SWS(Stabilized Water Solution) | CR | All | 40 |
| Sodium Bromate | CR | > 0.5 | 100 |
| Sodium Bromide | CR | > 0.5 | 100 |
| Sodium Carbonate | DSV | 10 | 65 |
| | DSV | 25 | 82 |
| | DSV | 32 | 80 |
| | CR | 35 | 80 |
| Sodium Carbonate/Sodium Bicarbonate | DSV | 20/15 | 80 |
| Sodium Chlorate | CR | 50 | 100 |
| | CR | 100 | 110 |
| Sodium Chloride | CR | > 0.5 | 100 |
| Sodium Chlorite | CR | 10 | 65 |
| | CR | 50 | 40 |
| Sodium Chlorite, pH > 6 | CR | All | 80 |
| Sodium Chromate | CR | 50 | 100 |

| | | | |
|---|------------|-------|-----|
| Sodium Cyanide | CR | All | 100 |
| Sodium Dichromate | CR | All | 100 |
| Sodium Diphosphate | CR | All | 100 |
| Sodium Dodecylbenzene Sulfonate | CR | All | 70 |
| Sodium Ferrocyanide | CR | All | 100 |
| Sodium Fluoride | CR | All | 80 |
| Sodium Fluoroborate | DSV | All | 90 |
| Sodium Fluorosilicate | DSV | All | 50 |
| Sodium Glycolate | CR | All | 100 |
| Sodium Hexametaphosphate | CR | All | 80 |
| Sodium Hydrogen | CR | All | 100 |
| Sodium Hydrosulfide | CR | All | 80 |
| Sodium Hydrosulfide(Sodium Bisulfide) | CR | All | 80 |
| Sodium Hydroxide | DSV+PC | 5 | 80 |
| | DSV+PC | 10 | 80 |
| | DSV+PC | 25 | 90 |
| | DSV+PC | 50 | 90 |
| Sodium Hypochlorite | DSV+PC | 5 | 65 |
| | DSV+PC | 21 | 80 |
| Sodium Hypochlorite, pH>11(active Chlorine) | PBPO - DSV | 24 | 0 |
| Sodium Lauryl Sulfate | CR | All | 70 |
| Sodium Metabisulfite | CR | All | 100 |
| Sodium Methyldithiocarbamate | CR | All | 80 |
| Sodium Monophosphate | CR | All | 100 |
| Sodium Myristyl Sulfate | CR | All | 70 |
| Sodium Nitrate | CR | All | 100 |
| Sodium Nitrite | CR | All | 100 |
| Sodium Oxalate | CR | All | 100 |
| Sodium Perchlorate | CR | 60 | 40 |
| Sodium peroxide A.S | CR | 100 | 25 |
| Sodium Persulfate | CR | All | 100 |
| Sodium Phosphate | CR | All | 100 |
| Sodium Phosphate, mono-,di-, tribasic | CR | > 0.5 | 100 |
| Sodium Polyacrylate | CR | All | 80 |
| Sodium Sarcosinate | CR | 40 | 50 |
| Sodium Silicate | CR | All | 100 |
| Sodium Sulfate | CR | All | 100 |
| Sodium Sulfide | CR | All | 100 |
| Sodium Sulfite | CR | All | 100 |
| Sodium Tartrate | CR | > 0.5 | 100 |
| Sodium Tetraborate | CR | All | 80 |
| Sodium Thiocyanate | CR | All | 80 |
| Sodium Thiosulfate | CR | All | 80 |
| Sodium Tripolyphosphate | CR | All | 100 |
| Sodium Xylene Sulfonate | CR | All | 70 |
| Solid iodine (adhesive) | CR | 100 | 25 |
| Sorbitol A.S | CR | 100 | 90 |
| Sorbitol Solutions | CR | All | 80 |
| Soy (Soya) Sauce | CR | 100 | 70 |
| Soya Oil | CR | 100 | 100 |
| Spearmint Oil | CR | 100 | 40 |
| Stannic Chloride | CR | All | 100 |

| | | | |
|---------------------------------|------------|----------|-----|
| Stannous Chloride | CR | > 0.5 | 100 |
| Stannous Chloride | CR | All | 100 |
| Starch A.S | CR | 100 | 90 |
| Steam, Dry, No Condensation | CR | 100 | 105 |
| Steam, Wet, Condensation | CR | 100 | 80 |
| Stearic Acid | CR | All | 100 |
| Sturated Aqueous Chlorine | CR | All | 100 |
| Styrene | CR | 100 | 50 |
| Styrene Acrylic Emulsion | CR | All | 50 |
| Styrene-Butadiene Latex | CR | All | 60 |
| Succinic acid A.S | CR | 100 | 80 |
| Succinonitrile, Aqueous | CR | All | 40 |
| Sugar Beet, Liquor | CR | All | 80 |
| Sugar Cane, Liquor & Sweetwater | CR | All | 80 |
| Sugar/Sucrose | CR | All | 100 |
| Sulfamic Acid | CR | 0.5 - 10 | 100 |
| | CR | 11-15 | 80 |
| | CR | 16 - 25 | 65 |
| | CR | 25 | 65 |
| Sulfanilic Acid | CR | All | 100 |
| Sulfanilic Acid (meta) | CR | > 0.5 | 100 |
| Sulfanilic Acid (para) | CCSR | All | 100 |
| Sulfonated Detergents | CR | 100 | 80 |
| Sulfur Chloride | CR | 100 | 0 |
| Sulfur Chloride | CR | Fumes | 90 |
| Sulfur Dioxide Dry or Wet | CR | Fumes | 100 |
| Sulfur Trioxide Gas | CR | Fumes | 100 |
| Sulfur Trioxide, Dry | CR | Fumes | 100 |
| Sulfur, Wettable, Fungicide | CCSR | All | 80 |
| Sulfuric Acid | CR | 0.5 - 25 | 105 |
| | DSV+ECR+CC | 25 | 100 |
| Sulfuric Acid | CR | 26 - 50 | 100 |
| | DSV+ECR+CC | 50 | 95 |
| | DSV+ECR+CC | 51 - 70 | 80 |
| | DSV+ECR+CC | 70 | 82 |
| | DSV+ECR+CC | 71 - 75 | 40 |
| | DSV+ECR+CC | 75 | 40 |
| | DSV+ECR+CC | 76 - 80 | 40 |
| | CCP | > 80 | 0 |
| Sulfuric Acid Gas | CR | vapor | 170 |
| Sulfuric Acid Gas | DSV+ECR+CC | Fumes | 170 |
| Sulfurous Acid | CR | 10 | 50 |
| Sulphonate de vinyle | CR | 100 | 25 |
| Sulphur dioxide | CR | 100 | 60 |
| Superphosphoric Acid, 76% P2O5 | CR | 100 | 100 |
| Surfactant, Anionic | CR | All | 50 |
| Tall Oil (Storage) | CR | 100 | 100 |
| Tall Oil Reactor | CU | 100 | 105 |
| Tallow/Sulfuric Acid | CR | 99/1 | 80 |
| Tannic Acid | CR | All | 100 |
| Tap Water, Hard | CR | All | 100 |
| Tap Water, Soft | CR | All | 80 |
| Tartaric Acid | CR | All | 100 |
| t-Butyl Methyl Ether (MTBE) | CR | 20 | 50 |

| | | | |
|--|-----|-----------|-----|
| | CR | 100 | 25 |
| Tetrabutyltin | CR | 100 | 50 |
| Tetrachloroethane | CR | 100 | 55 |
| Tetrachloroethylene(Perchloroethylene) | CR | 100 | 50 |
| Tetrachloropyridine | CR | 100 | 50 |
| Tetrahydrofuran | CR | 0-5 | 50 |
| | CR | 10 | 0 |
| | CR | 10-100 | 0 |
| Tetrahydrofuran, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Tetrahydrophthalic acid | CR | 100 | 40 |
| Tetramethyl Ammonium Hydroxide | DSV | 0 - 10 | 50 |
| Tetra-n-ButylphosphoniumHydroxide | DSV | 40 | 40 |
| Tetrapotassium Pyrophosphate | CR | 60 | 65 |
| | CR | 0 - 60 | 65 |
| TetrasodiumEthylenediaminetetraacetic Acid(Tetrasodium Salt of EDTA) | CR | All | 80 |
| Thionyl Chloride | CR | 100 | 0 |
| Thiourea | CR | 0 - 50 | 65 |
| Thyonil chloride | CR | 100 | 0 |
| Titanium Dioxide | CR | All | 80 |
| Titanium Dioxide/Sulfuric Acid | CR | 0 - 30/30 | 100 |
| Titanium Tetrachloride | CR | All | 80 |
| Tobias Acid (2-Naphthylamine-1Sulfonic) | CU | 100 | 100 |
| Toluene | CR | 100 | 50 |
| toluene Sulfonic Acid | CR | All | 100 |
| Toluene, Fumes, no condensationor coalescence | CR | Fumes | 60 |
| Toluidine (o-, p-, m-) | CR | 100 | 20 |
| Tomato Sauce | CR | All | 90 |
| Transformer Oils (Ester types) | CR | 100 | 65 |
| Transformer Oils (Silicone andMineral Oils) | CR | 100 | 150 |
| Tribasic Sodium | CR | All | 100 |
| Tributyl Phosphate | CR | 100 | 60 |
| Trichlorethylene | CR | 100 | 0 |
| Trichlorethylphosphate | CR | 100 | 25 |
| Trichloro Acetic Acid | CR | 50 | 100 |
| Trichloroethane | CR | 100 | 40 |
| Trichloroethylene | CR | 100 | 0 |
| Trichloromonofluoromethane(see Freon 11) | CR | 100 | 0 |
| Tricresyl Phosphate | CR | 100 | 70 |
| Triethanol Amine | CR | 100 | 50 |
| Triethylamine | CR | All | 50 |
| Triethylene Glycol(see Ethylene Glycol) | CR | 100 | 0 |
| Trifluoroacetic Acid(see Chloroacetic Acid) | CR | 100 | 0 |
| Trimethyl Ammonium Chloride(Trimethylamine HCl, TMAHCl) | CR | 70 | 50 |

| | | | |
|--|-----|--------|-----|
| Trimethyl Benzene | CR | 100 | 50 |
| Trimethylamine | CR | 20 | 50 |
| Trimethylamine | CR | 100 | 40 |
| Trimethylamine, Fumes,no condensation or coalescence | CR | Fumes | 80 |
| Trimethylene Chlorobromide | CR | 100 | 0 |
| Tri-n-propylamine | CR | 100 | 25 |
| Trioctylphosphate | CR | 100 | 60 |
| Tripropylene Glycol(see Ethylene Glycol) | CR | 100 | 0 |
| Trisodium Phosphate | CR | 100 | 120 |
| TRITON X-100 Wetting Agent(see Ethylene Glycol) | CR | 100 | 0 |
| Turpentine | CR | 100 | 100 |
| Uranium Extraction (see Kerosene) | CR | 100 | 0 |
| Urea | CR | 0 - 50 | 70 |
| Urea Formaldehyde Resin | CR | All | 50 |
| Urine (fresh) | CR | 100 | 25 |
| Vanillin Black Liquor | CR | 100 | 50 |
| Vegetale oil | CR | 100 | 100 |
| VERSENE 100 Chelating Agent(see also TetrasodiumEthylenediaminetetraacetic Acid) | CR | All | 80 |
| VERSENE Chelating Agents(others) | CR | All | 50 |
| Vinegar | CR | 100 | 100 |
| Vinyl Acetate | CR | 20 | 40 |
| | CR | 100 | 0 |
| Vinyl Chloride | CR | 100 | 0 |
| Vinyl Chloride Fumes,no condensation | CR | All | 80 |
| Vinyl polyacetate | CR | 100 | 25 |
| Vinyl propionate | CR | 100 | 0 |
| Vinylidene chloride | CR | 100 | 0 |
| Vinyltoluene | CR | 100 | 50 |
| VORANOL P-400 Polyol(see Ethylene Glycol) | CR | 100 | 0 |
| Water Deionized | CR | 100 | 80 |
| Water pure | CR | 100 | 90 |
| Water Vapor, Wet | CR | 100 | 80 |
| Water, Distilled | CR | 100 | 80 |
| Water, Phenol (see Phenol) | CR | 100 | 0 |
| Water, Sea, Desalination | CR | All | 80 |
| Water, Steam Condensate | CR | 100 | 80 |
| Water, Tap, Hard | CR | 100 | 100 |
| Water, Tap, Soft | CR | 100 | 80 |
| Whey | CR | All | 65 |
| White Liquor (Pulp Mill) | DSV | All | 80 |
| Wine | CR | 100 | 25 |
| Xylene | CR | 100 | 50 |
| Xylene, Fumes, No Condensationor Coalescence | CR | Fumes | 80 |
| Zinc Chloride | CR | 100 | 120 |
| Zinc Nitrate | CR | 100 | 120 |
| Zinc Phosphate (slurry) | CR | > 0.5 | 80 |
| Zinc Sulfate | CR | All | 120 |